Brass

NATURAL

NATURAL

CHARACTERISTICS		EQUIVALENTS				CHEMICAL ANALYSIS (%)					
Tensile Strength (MPa)	380	ASTM	AISI	BS	UNS		Cu	Al	Zn	Pb	
				CZ121	C38510	MIN	56	-	Remainder	2.5	
Hardness Supplied (HB)	85 - 110					MAX	60	-	Remainder	4.5	
		NOTES									
Machinability Rating %		NOTES C38510 brass will weather to a warm bronze colour. It has good corrosion									

DESCRIPTION

Free Cutting brass is significantly improved form of 60/40 brass. Uniform lead distribution suppresses the brittle phases which cause tool wear.

APPLICATIONS

resistance to fresh water but should not be used in contact with ammonia compounds or be immersed in salt water.

> Builders hardware and architectural application in sections. Electrical connections. Nuts, bolts and screw threads.

WARNING: While all care has been taken to provide accurate information here, it should be noted that it is for a quide only and any information must be checked by the manufacturer before being relied upon.

EDCON

Sydney Metro

Blacktown Brookvale Revesby

15 Garling Road Kings Park 10/9-13 Winbourne Road Brookvale 122 Milperra Road Revesby

Rural

Bathurst Orange

51 Sydney Road Raglan 23 Leewood Drive Orange

1300 233 266 edconsteel.com.au