LG2 Bronze

VIOLET

VIOLET

CHARACTERISTICS		EQUIVALENTS				CHEMICAL ANALYSIS (%)					
Tensile Strength (Mpa)	200 - 270	ASTM	AISI	BS	JIS		Cu	Sn	Zn	Pb	
		SAE 40		1400	BC6C		85	5	5	5	
Hardness Supplied (HB)	80 - 66	C83600		LG2-C							
		NOTES									
Machinability Rating %	178	Commonly known as Lead Gunmetal. May be used for Phosphor Bronze (PB1) applications.									
DESCRIPTION Continuous Cast Bronze Bar, also available in Hollow Bars. Continuously cast bar has greatly improved physical properties compared to normal sand cast material due to the elimination of inclusions.		APPLICATIONS General purpose bearing, hydraulic components, Gears, Worm Wheels, Valve seats, slide valves, rollers, wear rings.									

WARNING: While all care has been taken to provide accurate information here, it should be noted that it is for a guide only and any information must be checked by the manufacturer before being relied upon.



Sydney Metro

Blacktown Brookvale Revesby 15 Garling Road Kings Park 10/9-13 Winbourne Road Brookvale 122 Milperra Road Revesby

Rural

Bathurst Orange 51 Sydney Road Raglan 23 Leewood Drive Orange

1300 233 266 edconsteel.com.au