C250LO (Hollow Sections)

Colour coded for thickness

Colour coded for thickness

CHARACTERISTICS				CHEMICAL ANALYSIS (%)									
Tensile Strengt	h (MPa)		320		С	Si	Mn	Р	S	Al	CE*		
			320		0.04	0.005	0.19	0.006	0.005	0.015	0.07		
Yield Strength	(Mpa)		250		0.07	0.02	0.3	0.018	0.018	0.06	0.12		
			230	NOTES									
				*CE stands for carbon equivalent which is a calculation on an actual composition using a formula. Steel with CE less than 0.39 in general to not require preheat.									

DESCRIPTION

This is the most common grade that Medium to Extra Heavy wall pipe will be supplied as. Extra Light and Light pipe typically conforms to C350LO

APPLICATIONS

Handrails, Bollards, Power Poles

WARNING: While all care has been taken to provide accurate information here, it should be noted that it is for a guide only and any information must be checked by the manufacturer before being relied upon.

EDCON STIEL

Sydney Metro

Blacktown Brookvale Revesby 15 Garling Road Kings Park 10/9-13 Winbourne Road Brookvale 122 Milperra Road Revesby

Rural

Bathurst Orange 51 Sydney Road Raglan 23 Leewood Drive Orange 1300 233 266 edconsteel.com.au